

Pale Oil 60

Specification

PARAMETERS	TEST METHOD	UNITS	GUARANTEED	TYPICAL
Color ASTM	ASTM D 6045	-	Max 0,5	L0,5
Kinematic viscosity at 40 °C	ASTM D 445	mm ² /s	9.50-11.50	11.03
Kinematic viscosity at 100 °C	ASTM D 445	mm ² /s	Report	2.49
Pour point	ASTM D7346	°C	Max -46	-57
Flash point (COC)	ASTM D 93	°C	Min 143	146
Density at 15 °C	ASTM D 4052	kg/m ³	Report	0,91
Sulfur	ASTM D 2622	mg/kg	Max 100	26
API Gravity, 60F	ASTM D 4052	F		24.2
Specific Gravity	ASTM D 4052	F	0.887-0.912	0.909
Aniline Point	ASTM D 611	°C	63-66	64
Refractive Index	ASTM D 1747			1.4949