

Pale Oil 2000

Specification

PARAMETERS	TEST METHOD	UNITS	GUARANTEED	TYPICAL
Color ASTM	ASTM D 6045	-	3.0	L2.5
Kinematic viscosity at 40 °C	ASTM D 445	mm ² /s		3994
Kinematic viscosity at 100 °C	ASTM D 445	mm ² /s	38.00-42.00	39.2
Pour point	ASTM D7346	°C	Max 29	
Flash point (COC)	ASTM D 93	°C	Min 229	233
Density at 15 °C	ASTM D 4052	kg/m ³	Report	0,968
Sulfur	ASTM D 2622	wt%	Max 500	
API Gravity, 60F	ASTM D 4052	F		14.9
Specific Gravity	ASTM D 4052	F	0.927-0.973	0.967
Aniline Point	ASTM D 611	°C	77-82	79
Refractive Index	ASTM D 1747			1.5264