

Pale Oil 500

Specification

PARAMETERS	TEST METHOD	UNITS	GUARANTEED	TYPICAL
Color ASTM	ASTM D 6045	-	2.5	L0.5
Kinematic viscosity at 40 °C	ASTM D 445	mm ² /s	220.00-400.00	313
Kinematic viscosity at 100 °C	ASTM D 445	mm ² /s		12.4
Pour point	ASTM D7346	°C	Max -1.1	
Flash point (COC)	ASTM D 93	°C	Min 205	224
Density at 15 °C	ASTM D 4052	kg/m ³	Report	0,95
Sulfur	ASTM D 2622	wt%	Max 200	
API Gravity, 60F	ASTM D 4052	F		17.7
Specific Gravity	ASTM D 4052	F	0.939-0.955	0.949
Aniline Point	ASTM D 611	°C	68-77	73
Refractive Index	ASTM D 1747			1.5166