

Base Oil 300N

Specification

PARAMETERS	TEST METHOD	UNITS	GUARANTEED	TYPICAL
Appearance	Visual	-	C&B	C&B
Color ASTM	ASTM D 1500	-	Max 0,5	L0,5
Kinematic viscosity at 40 °C	ASTM D 445	mm ² /s	Report	52,88
Kinematic viscosity at 100 °C	ASTM D 445	mm ² /s	Report	7,6
Viscosity index	ASTM D 2270	-	100-119	108
Pour point	ASTM D 5950	°C	Max -15	-22
Flash point (COC)	ASTM D 92	°C	Min 210	230
Density at 15 °C	ASTM D 4052	kg/m ³	Report	0,8637
Sulfur	ASTM D 5453	wt%	0,001	0,00016
Aromatics	ASTM D 7419	wt%	Max 1.0	0,2
Saturates	ASTM D 7419	wt%	99	99,80