

# PAO 4cSt

## Isoparaffinic Polyalphaolefin

### Specification

PARAMETERS	TEST METHOD	UNITS	TYPICAL
Kinematic viscosity at 100 °C	ASTM D7042 or D445	mm <sup>2</sup> /s	3.85
Kinematic viscosity at 40 °C	ASTM D7042	mm <sup>2</sup> /s	16.8
Pour point °C	ASTM D5950	°C	-72
Flash point °C	ASTM D92	°C	217
Fire point °C	ASTM D92	°C	253
Density at 20°C	ASTM D7042	lb/gal	6.835
Volatility, NOACK	ASTM D5800	Wt. %	13.3
Viscosity index	ASTM D2270	-	124