

Base Oil 6cSt

Specification

PARAMETERS	TEST METHOD	UNITS	GUARANTEED	TYPICAL
Appearance	ASTM D 4176	-	C&B	C&B
Color	ASTM D 1500	-	Max 0.5	L0.5
Kinematic viscosity at 40 °C	ASTM D 445	mm ² /s	-	36.00
Kinematic viscosity at 100 °C	ASTM D 445	mm ² /s	5.5 – 6.5	6.30
Viscosity index	ASTM D 2270	-	Min 120	125
Pour point	ASTM D 6749	°C	Max -15	-18
Flash point COC	ASTM D 92	°C	-	258
Sulfur	ASTM D 5453	wtppm	Max 10	2.0
NOACK	ASTM D 5800	wt %	Max 8.5	8.0